

TECHNICAL DATA

MONO[®]

MONO ULTRA[™] BATH & KITCHEN SEALANT

Revised: 3/12/10

MONO Ultra[®] Bath & Kitchen Sealant – White and Colors

- **Waterproof Seal**
- **Mildew Resistant**
- **Easy water clean-up**
- **Paintable**
- **Superior Adhesion**
- **Skins Quickly**
- **Low Odour**

Packaging: 300 mL cartridge, 150 mL squeeze tube
Color: White, Bone
DAP UPC Number: 0 70798 75561 1, 0 70798 75563 5, 0 70798 75587 1, 0 70798 75590 1
MONO Product Code: 0 63213 00561 3, 0 63213 00563 7, 0 63213 00587 3, 0 63213 00590 3
MONO Model: 967806312, 967859312, 967806106, 967859106

Company Identification:

Manufactured For: DAP Canada, 475 Finchdene Square, Unit 5, Scarborough, ON M1X 1B7
Usage Information: Call 1-888-327-8477 or visit monosealants.ca
Order Information: 416-321-1522
Fax Number: 416-321-3325

Product Description:

MONO Ultra[®] Bath & Kitchen is a latex-based sealant that provides a durable, waterproof seal in bathroom and kitchen applications. Easy to gun, low odour, mildew resistant, outstanding flexibility and superior adhesion. Paintable and cleans up easily with soap and water.

Suggested Uses:

Ideal for Caulking and Sealing:

- *Showers*
- *Acrylic shower inserts*
- *Sinks*
- *Tubs*
- *Countertops*
- *Backsplashes*
- *Bathroom fixtures*
- *Kitchen fixtures*
- *Toilets*

Outstanding adhesion to:

- *Ceramic Tile*
- *Porcelain*
- *Metal*
- *Painted Surfaces*
- *Plastic Tile*
- *Cultured Marble*
- *Drywall*
- *Glass*
- *Wood*
- *Fiberglass*

Surface Preparation & Application:

1. All surfaces must be clean, dry and completely free of old caulk.
2. Do not use for water-submerged applications.
3. Apply at temperatures above 5°C (40°F).
4. Remove cap (from tube). Trim nozzle at 45° angle to desired bead size.
5. Load into caulking gun if using the 300 mL cartridge.
6. Fill gap with sealant, pushing sealant ahead of nozzle.
7. Smooth bead.
8. Joint width should not exceed 9.5 mm (3/8"). If joint depth exceeds 9.5 mm (3/8"), use backer rod material.
9. Clean up excess uncured sealant with damp sponge before it skins over. Scrape or cut away excess cured sealant.
10. Allow sealant to dry at least 2 hours (longer in cool/humid conditions) before painting with a latex or oil-based paint.
11. Reseal for storage and reuse.

For best results:

- *Apply in temperatures above 5°C (40°F).*
- *Not for continuous underwater use.*
- *Allow sealant to dry at least 2 hours (longer in cool or humid conditions) before painting with a latex or oil-based paint.*
- *Allow sealant to dry fully (at least 24 hours) before exposing to water and moisture.*
- *Store product away from extreme heat or cold.*

Physical & Chemical Characteristics:

Tooling Time:	10 minutes
Tack Free Time:	30 minutes
Paintable:	Yes
Odor:	Very Mild
Consistency:	Smooth and Creamy
Vehicle:	Acrylic Polymer
Volatile:	Water
Flash Point:	None
Filler:	Calcium Carbonate
Density:	1.05 ± 0.01
Solids:	59% ± 1.0% by weight
Weight per Gallon:	1.05 ± .01 kg/L (8.8 ± 0.05 lbs/gal)
Service Temperature:	-34°C to 82°C (-30°F to 180°F)
Application Temperature:	4°C to 38°C (40°F to 100°F)
Freeze Thaw Stability:	Passes 5 Cycles
Shelf Life:	12 Months
Coverage:	150 mL: 9 metres at 4.76 mm bead (30 linear ft. at a 3/16" diameter bead) or 2 average size bathtubs. 300 mL: 17 metres at 4.76 mm bead (56 linear feet at a 3/16" diameter bead) or 4 average size bathtubs.
MSDS No:	00042375603

Clean Up:

Before curing, remove excess sealant with a damp cloth. After product has cured, excess sealant must be cut or scraped away.

Safety:

See product label or Material Safety Data Sheet (MSDS) for safety information. You can request an MSDS by visiting our website at monosealants.ca or by calling 416-321-1522.

Satisfaction Guarantee:

If not satisfied with product performance when used as directed within one year of purchase, return used container and sales receipt to DAP Canada, 475 Finchdene Square, Unit 5, Scarborough, ON. M1X 1B7 for product replacement or sales price refund. DAP Canada and its affiliates will not be liable for any incidental or consequential damages under any circumstances.